

Physiologically acceptable films, including edible films, are disclosed. The films include a water soluble film-forming polymer, such as pullulan, and a taste masked pharmaceutically active agent, such as dextromethorphan. The taste masking agent is preferably a sulfonated polymer ion exchange resin comprising polystyrene cross-linked with divinylbenzene, such as AMBERLITE. Methods for producing the films are also disclosed.